

KAYU™ - Decking

Density Comparison Guide

Wood/Source	LBS/CU FT	KG/M3
Batu (RB) – Indonesia	60	960
Membatu (RB) - Malaysia	54	865
Bangkirai (YB) – Indonesia	64	1020
Kapur – Indonesia	53	830
Bukit (DRM) - Malaysia	53	830
IPE – Brazil	66	1050
Cumaru - Brazil	67	1070
Western Red Cedar – USA / Canada	33	530
Douglas Fir – USA / Canada	48	770
Redwood - USA	40	640

Sources:

- Malaysian Timber Industry Board
- Malaysian Timber Council
- Department of Forestry Indonesia
- International Tropical Timber Organization
- Center Technique Forestier Tropical
- US Department of Agriculture